



9773

Light-Cure BGA, CSP Ruggedized Adhesive

APPLICATIONS

- Reinforcement of Fine-Pitch or Leadless Components on Printed Circuit Boards
- Ruggedization/Staking Material
- Shock Absorption
- Underfill Alternative
- Encapsulant

FEATURES

- UV/Visible Light Cure
- Low Outgassing
- Low Ionic Content Compliance with Mil-Std 883 Method 5011
- High Viscosity
- Halogen Free
- Silicone Free
- No Solvents Added

OTHER FEATURES

- Mil Std 883 Method 5011 Compliant
- Adhesion to Various PCB Substrates
- Meets ASTM E595 Low Outgassing
- NASA MAPTIS Listed (Material Code 09907)
- Slump Resistance @ 90° up to 72 hours
- 23 Gauge Needle Tip Minimum for Dispensing
- Jetting Compatible

Dymax 9773 is a low outgassing, low ionic content, high-performance light-cure staking/ruggedizing material especially formulated to stabilize critical components on printed circuit boards in missiles, satellites, and spacecraft. This material is designed for rapid on-demand broad-spectrum curing. Dymax staking materials contain no nonreactive solvents and cure upon exposure to light. The ability of Dymax materials to cure in seconds enables faster processing, greater output, and lower processing costs. When cured with Dymax light-curing spot lamps, focused-beam lamps, or flood lamps, they deliver optimum speed and performance for printed circuit boards. Dymax lamps offer the ideal balance of UV and visible light for the fastest, deepest cures. This product is in full compliance with RoHS directives 2015/863/EU.

UNCURED PROPERTIES *

Property	Value	Test Method
Solvent Content	No Nonreactive Solvents	N/A
Chemical Class	Acrylated Urethane	N/A
Appearance	Off-White to Slate Grey Translucent Gel	N/A
Soluble in	Organic Solvents	N/A
Density, g/ml	1.35	ASTM D1875
Viscosity, cP	54,000	ASTM D2556
Shelf Life at Recommended Conditions from Date of Manufacture	7 months	N/A

CURED MECHANICAL PROPERTIES *

Property	Value	Test Method
Durometer Hardness	D47	ASTM D2240
Tensile at Break, MPa [psi]	12.0 [1700]	ASTM D638
Elongation at Break, %	85	ASTM D638
Modulus of Elasticity, MPa [psi]	103 [15000]	ASTM D638
Glass Transition T _g , °C	45	ASTM D5418
CTE _{a1} , mm/m/°C	77	ASTM E831
CTE _{a2} , mm/m/°C	150	ASTM E831

OTHER CURED PROPERTIES *

Property	Value	Test Method
Boiling Water Absorption, % (2 h)	0.6	ASTM D570
Water Absorption, % (25°C, 24 h)	0.2	ASTM D570
Linear Shrinkage, %	0.6	ASTM D2566
Outgassing – Total Mass Loss (TML), %	0.86	ASTM E595
Outgassing – Collected Volatile Condensable Material (CVCM), %	0.04	ASTM E595
Thermal Stability @ 200°C	Passes	Mil-Std 883 Method 5011
Ionic Content	Passes	Mil-Std 883 Method 5011
Bond Strength @ RT after 1000hrs. @ 150°C	Passes	Mil-Std 883 Method 5011
Thermal Conductivity	Passes	Mil-Std 883 Method 5011
Thermal Conductivity	Passes	ASTM E1530-19/Mil-Std 883 Method 5011
Volume Resistivity	Passes	Mil-Std 883 Method 5011
Dielectric Constant & Dissipation Factor	Passes	Mil-Std 883 Method 5011

* Not Specifications

N/A Not Applicable

© 2025 Dymax Corporation. All rights reserved.

All trademarks in this guide, except where noted, are the property of, or used under license by Dymax Corporation, U.S.A.

Technical Data Collected 1/27/2023 Rev.09/18/2025

ELECTRONIC ASSEMBLY/ CIRCUIT BOARD MATERIALS
 9773 Staking/Encapsulant/Ruggedizing Product Data Sheet



ADHESION	
Substrate	Recommendation
PCB	✓
Silicon	✓
Leadframe	✓
Ceramic	✓

✓ Recommended ○ Limited Applications
 st Requires Surface Treatment (e.g. plasma, corona treatment, etc.)

ELECTRICAL PROPERTIES *		
Property	Value	Test Method
Volume Resistivity, ohm-cm	1.27E+14	ASTM D257
Surface Resistivity, ohm	1.14E+12	ASTM D257
Dielectric Constant, 1 MHz	4.46	ASTM D150
Dissipation Factor, 1 MHz	0.023	ASTM D150
Dielectric Strength, V/mil	739	ASTM D149
Dielectric Breakdown Voltage, kV [V]	31.8 [38,000]	ASTM D149

CURING GUIDELINES

UV-curing guidelines for 9773 at 2.5 mm thickness:

Dymax Curing System (Intensity)	Cure Time or Belt Speed
BlueWave® 200 (10 W/cm ²) ^A	4 s
UVCS Conveyor with Fusion F300S (2.5 W/cm ²) ^B	3m/min [10ft/min]



^A Intensity was measured over the UVA range (320-395 nm) using a Dymax ACCU-CAL™ 50 Radiometer.

^B Intensity was measured over the UVA range (320-395 nm) using a Dymax ACCU-CAL™ 160 Radiometer.

^C Intensity was measured over the UVA/Visible range (350-450 nm) using a Dymax ACCU-CAL™ 50-LED Radiometer.

DEPTH OF CURE

The graph below shows the increase in depth of cure as a function of exposure time. A 9.5 mm [0.37 in] diameter specimen was cured in a polypropylene mold and cooled to room temperature. It was then released from the mold and the cure depth was measured.





OPTIMIZING PERFORMANCE AND HANDLING

1. This product cures with exposure to UV and visible light. Exposure to ambient and artificial light should be kept to a minimum before curing. Dispensing components including needles and fluid lines should be 100% light blocking, not just UV blocking.
2. All bond surfaces should be clean and free from grease, mold release, or other contaminants prior to dispensing the material.
3. Cure speed is dependent upon many variables, including lamp intensity, distance from the light source, required depth of cure, bond gap, and percent light transmission of the substrate.
4. Oxygen in the atmosphere may inhibit surface cure. Surfaces exposed to air may require high-intensity UV light to produce a dry surface cure. Flooding the bond area with an inert gas, such as nitrogen, can also reduce the effects of oxygen inhibition.
5. Parts should be allowed to cool after cure before testing and subjecting to any loads.
6. In rare cases, stress cracking may occur in assembled parts. Three options may be explored to eliminate this problem. One option is to heat anneal the parts to remove molded-in stresses. A second option is to open the gap between mating parts to reduce stress caused by an interference fit. The third option is to minimize the amount of time the liquid material remains in contact with the substrate(s) prior to curing.
7. Light curing generally produces some heat. If necessary, cooling fans can be placed in the curing area to reduce the heating effect on components.
8. At the point of curing, an air exhaust system is recommended to dissipate any heat and vapors formed during the curing process.

STORAGE AND SHELF LIFE

Store the material in a cool, dark place when not in use. Do not expose to light. This product may polymerize upon prolonged exposure to ambient and artificial light. Keep covered when not in use. This material shelf life noted on page 1 of this document, when stored between **10°C (50°F) and 32°C (90°F)** in the original, unopened container.

CLEANUP

Uncured material may be removed from dispensing components and parts with organic solvents. Cured material will be impervious to many solvents and difficult to remove. Cleanup of cured material may require mechanical methods such as ultrasonic bath, water jet, vacuum tweezers, air knife, and/or warming to aid in the removal.

ELECTRONIC ASSEMBLY/ CIRCUIT BOARD MATERIALS

9773 Staking/Encapsulant/Ruggedizing Product Data Sheet



GENERAL INFORMATION

This product is intended for industrial use only. Keep out of the reach of children. Avoid breathing vapors. Avoid contact with skin, eyes, and clothing. Wear impervious gloves. Repeated or continuous skin contact with uncured material may cause irritation. Remove material from skin with soap and water. Never use organic solvents to remove material from skin and eyes. For more information on the safe handling of this material, please refer to the Safety Data Sheet before use.

The data provided in this document are based on historical testing that Dymax performed under laboratory conditions as they existed at that time and are for informational purposes only. The data are neither specifications nor guarantees of future performance in a particular application. Dymax does not guarantee that this product's properties are suitable for the user's intended purpose.

Numerous factors—including, without limitation, transport, storage, processing, the material with which the product is used, and the ultimate function or purpose for which the product was obtained—may affect the product's performance and/or may cause the product's actual behavior to deviate from its behavior in the laboratory. None of these factors are within Dymax's control. Conclusions about the behavior of the product under the user's particular conditions, and the product's suitability for a specific purpose, cannot be drawn from the information contained in this document.

It is the user's responsibility to determine (i) whether a product is suitable for the user's particular purpose or application and (ii) whether it is compatible with the user's intended manufacturing process, equipment, and methods. Under no circumstances will Dymax be liable for determining such suitability or compatibility. Before the user sells any item that incorporates Dymax's product, the user shall adequately and repetitively test the item in accordance with the user's procedures and protocols. Unless specifically agreed to in writing, Dymax will have no involvement in, and shall under no circumstances be liable for, such testing.

Dymax makes no warranties, whether express or implied, concerning the merchantability of this product or its fitness for a particular purpose. Nothing in this document should be interpreted as a warranty of any kind. Under no circumstances will Dymax be liable for any injury, loss, expense or incidental or consequential damage of any kind allegedly arising in connection with the user's handling, processing, or use of the product. It is the user's responsibility to adopt appropriate precautions and safeguards to protect persons and property from any risk arising from such handling, processing, or use.

The specific conditions of sale for this product are set forth in Dymax's [General Terms & Conditions of Sale](#). Nothing contained herein shall act as a representation that the product use or application is free from patents owned by Dymax or any others. Nothing contained herein shall act as a grant of license under any Dymax Corporation Patent.

Except as otherwise noted, all trademarks used herein are trademarks of Dymax. The "®" symbol denotes a trademark that is registered in the U.S. Patent and Trademark Office.

The contents of this document are subject to change. Unless specifically agreed to in writing, Dymax shall have no obligation to notify the user about any change to its content.

CONTACT DYMAYX

www.dymax.com

Americas

USA | +1.860.482.1010 | info@dymax.com

Mexico | +1.915.315.9381 | info-LATAM@dymax.com

Europe

Germany | +49 611.962.7900 | info_de@dymax.com

Ireland | +353 21.237.3016 | info_ie@dymax.com

Asia

Singapore | +65.67522887 | info_ap@dymax.com

Shenzhen | +86.755.83485759 | info@hanarey.com

Hong Kong | +852.2460.7038 | dymaxasia@dymax.com

Korea | +82.31.608.3434 | info_kr@dymax.com